

TABLE 2. The Effect of Lead-free Assembly and Rework on Marginal Microvias

IST THERMAL CYCLES TO FAILURE – VARIOUS PRECONDITIONING			
	AS RECEIVED	6 X 230°C	6 X 260°C
Mean	788	443	4
Minimum	375	204	2
Maximum	925	925	5