

TABLE 4. Materials evaluated through IST testing.

Product	Description	Glass Transition Temp., °C	Decomposition Temp., °C	% Expansion, 50-260°C (40% Resin Content)
C	Conventional High-Tg	175	310	3.5
D*	High-Tg/High-Td	175	335	3.4
D	High-Tg/High-Td/Reduced CTE	175	335	2.7